

PRODUCT DATA SHEET

Sikalastic®-690 Rapid

SINGLE COMPONENT RAPID-DRY HIGHLY ELASTIC POLYURETHANE ONE COAT WATERPROOFING MEMBRANE

DESCRIPTION

Sikalastic®-690 Rapid is a solvent-free single component, fast drying, seamless liquid applied polyurethane waterproofing membrane for old and new roofs as an exposed system. Sikalastic®-690 Rapid is available in various colours, making it ideal for waterproofing of concrete flat roof area.

USES

- As exposed or concealed waterproofing system on roofs, podiums, balconies, bathrooms, pools, tanks and planters
- As waterproofing coat for external wall, basements and foundations
- As water barrier under plasters, screeds or tiles
- Refurbishment of metal roof, old tile surfaces, concrete roofs and concrete gutters without the need to hack
- As exposed waterproofing in submerged areas like ponds and fountains when fully cured

CHARACTERISTICS / ADVANTAGES

- Excellent adhesion on concrete, render and masonry
- One continuous waterproofing system for all exposed area
- Rapid drying and curing
- Allows for high build up thickness to overcome unevenness of roof surfaces.
- High productivity and reducing the risk of membrane being wash out due to sudden occurrence of rain during application
- High crack bridging ability
- Good resistant to UV, chemical, mould and fungus.
- Solvent-free and low VOC
- Available in various colours

PRODUCT INFORMATION

Chemical Base	Polyurethane
Packaging	25 kg per pail
Shelf Life	12 months from date of production
Storage Conditions	Stored properly in undamaged and unopened original sealed packaging in cool and dry conditions. Protect from direct sunlight and frost.
Colour	Black, Grey and White (other colour on request)
Density	Approx. 1.3 kg/litre

TECHNICAL INFORMATION

Tensile Strength	>3.0 Mpa	(ASTM D412-16)
Elongation at Break	Elongation at break > 400%	(ASTM D412-16)
	Recovery for 350% Elongation : 295 %	(ASTM D412-16)

SYSTEM INFORMATION

System Structure

STANDARD COATINGS SYSTEM

~ 2.0 kg/m² in one or more coats (DFT@ ~ 1.5 mm)

REINFORCED COATING SYSTEM

Coating System	Product	System
Primer Coat*	Sikalastic® -500 Acrylic Primer HK/ Sikafloor® -156/ Sikafloor® -01 Primer TH	~ 0.1-0.2 kg/m ²
Base Coat	Sikalastic®-690 Rapid	~ 1.5 kg/m ²
Reinforcement	Sikalastic® Fleece -80/ Sika® Glass Fabric 55G	
Top Coat	Sikalastic®-690 Rapid	~ 1.0 kg/m ²

(Total DFT of coating system @ ~ 2.0 mm)

*For exposed system or on very absorbent surfaces only

*For roof refurbishment direct apply Sikalastic®-690 Rapid on top of existing tiles, use Sikafloor®156 as primer.

*Sikafloor®-01 Primer TH dilute with water 1:2 consumption at ~ 7-8 m²

- Alternative Sika reinforcement options can be used.
- These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level and wastage etc.

APPLICATION INFORMATION

Ambient Air Temperature	5°C to 40°C
Tack Free Time	Approx. 1 hour (@ 25 oC & RH 75 % for foot traffic)
Drying Time	1–4 hours depend on the coating thickness and temperature of substrate

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

- Do not apply at ambient and substrate temperature less than 5 °C
- Do not apply directly to wet and damp surface
- Do not thin with water or other solvents
- Do not apply to areas when rain is imminent
- Ensure adequate ventilation during application
- Allow 3 days (@25 °C & RH 75%) drying period before flood test on treated area. For situations of low temperature or high humidity, allow longer drying time
- For damp substrate (not fully cured), a moisture barrier coat should be applied prior to the application of

Sikalastic®-690 Rapid

- For metal, bitumen and asphalt surface, a barrier primer should be applied. Please contact Sika Technical Services for more details

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

VOC Data

VOC content (ready to use) not exceeding 50g/litre [Type of regulated paint under the Air Pollution Control (volatile organic compounds) Regulation of Hong Kong: (Roof coating (exposed)]

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

All substrates must be structurally sound, stable, dry and clean (compressive strength : min. 25 N/mm² and cohesive strength : min. 1.5 N/mm²). Smooth shiny surfaces are to be roughened while uneven surface to be leveled or filled first. All surfaces should be free of sharp protrudings, loose materials, de-bonded coatings, curing membranes, release agents, wax residues, laitance, algae and moss, oils, dust, etc. Structurally unsound layers and surface contaminants are to be mechanically removed by abrasive blasting, blast tracking, grinding or equivalent methods. Cracks and faulty joints should be repaired.

APPLICATION

Priming

On very absorbent surfaces, a primer coat (Sikalastic®-500 Acrylic Primer HK) should be applied on the concrete surface prior to the application of waterproofing membrane. Care should be taken to ensure the required membrane final dry film thickness is achieved.

Application Method / Tool

Sikalastic®-690 Rapid can be applied by brush, roller, trowel, squeegee or airless spray directly onto the treated substrate. Apply subsequent coats at different directions to the previous coat. Before applying any coating, the previous coat must be touch dry. Subsequent coats should be applied within a max. period of 24 hours. The finished membrane should be protected from damage by other trades. The reinforcement, Sika® Glass Fabric 55G or Sikalastic® Fleece-80 should be pressed into the 1st coat of Sikalastic®-690 Rapid whilst it is still wet. Depending on the ambient temperature within an hour, the 1st coat will be foot trafficable. Then apply another 1 or 2 coats of Sikalastic®-690 Rapid to completely cover the reinforcement.

CLEANING OF TOOLS

Clean all tools and application equipment with Sika® Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

CLEANING

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.



Product Data Sheet
Sikalastic®-690 Rapid
February 2024, Version 02.03
020915205000000087

Sikalastic-690Rapid-en-HK-(02-2024)-2-3.pdf